

#### WHERE TO USE

**Nivoplan** is particularly suitable for rendering and levelling indoor and outdoor wall and ceiling surfaces in layers of thicknesses from 2 to 30 mm.

**Nivoplan** makes the surfaces suitable for the installation of ceramic tiles or for paint finishing.

#### Some application examples

- Smoothing walls prior to installing ceramic tiles;
- Repairing old, damaged renders.
- Levelling reinforced concrete surfaces of swimming pools and façades prior to installing ceramic coverings, waterproofing by painting.
- Smoothing foamed cement, brick, eraclit, etc. walls.

### **TECHNICAL CHARACTERISTICS**

**Nivoplan** is a grey or white powder composed of cement, selected aggregates and special synthetic resins which, mixed with water, provide a mix that is easy to apply on vertical surfaces with a trowel or with a rendering spraying machine.

**Nivoplan**'s bonding properties can be improved by adding **Planicrete** and water to the product during mixing, approximately 2 litres per bag (used as a partial replacement for the mix water).

The addition of **Planicrete** is necessary for thin applications over concrete or in cases where the render will receive tile or natural stone coverings.

#### **RECOMMENDATIONS**

- Nivoplan must never be used on gypsum or gypsum-based surfaces, unless those surfaces have been prepared with a coat or two of Primer G (see relative Technical Data Sheet);
- Nivoplan is not suitable for smoothing over floors due to its limited compressive strength. In this case, please refer to the Technical Data Sheets regarding products for preparing substrates, or contact the MAPEI Technical Assistance Department.

## APPLICATION PROCEDURE Preparing the substrate

The substrate must be compact, free of dust, loose parts and clean from oils, grease, paint or glue residues.

**Nivoplan** can also be applied to damp surfaces without any problem, but cure time will be slightly prolonged.

It is advisable to wet highly absorbent substrates (brick, foamed cement, etc.) before applying **Nivoplan**, especially if the layer is less than 3 mm thick.

# Nivoplan



Mixing with a mini cement-mixer



Restoring old brickwork



Levelling with a laying-on trowel

TECHNICAL DATA (typical values)			
PRODUCT IDENTITY			
Consistency:		powder	
Colour:		grey and white	
Density (kg/m³):		1,400	
Dry solids content or active substance (%):		100	
Storage:		12 months in a dry place in original packaging	
Hazard classification according to EC 1999/45:		irritant none Before using refer to the "Safety instructions for preparation and application" paragraph and the information on the packaging and Safety Data Sheet	
Customs class:		3824 50 90	
APPLICATION DATA (at +23°C - 50% R.H.)			
Mix ratio:		25 parts water per 100 parts of <b>Nivoplan</b> by weight	
Consistency of mix:		very pasty	
Density of mix (kg/m³):		1,830	
pH of mix:		approx. 12	
Pot life:		2-3 hours	
Application temperature range:		from +5°C to +30°C	
Thickness possible for one coat (mm):		from 2 to 30	
Waiting time before bonding:		> 4 hours dependant on thickness and temperature	
Waiting time before painting:		at least 14 days	
FINAL PERFORMANCES			
Resistance to alkalis:		excellent	
Resistance to oils:		excellent (poor to vegetable oils)	
Resistance to solvents:		excellent	
Temperature range when in use:		from –30°C to +90°C	
Compatibility with adhesives:		excellent	
Flexural strength (N/mm²):		3.5	
Compressive strength (N/mm²):		6.0	
Performance characteristic	Test method	Requirements according to EN 998-1 type GP-CSIV	Performance of product
Compressive strength (MPa):	EN 1015-11	≥ 6 category CS IV	≥ 12 category CS IV
Bond strength on brickwork (MPa):	EN 1015-12	not required	≥ 1.0 FP: B
Water absorption (kg/(m²·minº.5):	EN 1015-18	WO (not specified) W1 (≤ 0.40) W2 (≤ 0.20)	W1 (< 0.4)
Thermal conductivity -λ- (W/m · K°):	EN 1745	not required	0.95
Reaction to fire:	Euroclass	Class declared by manufacturer	A1

**Nivoplan** cannot be used on gypsum surfaces and the like, unless they are treated beforehand with **Primer G**.

#### **Preparing the mix**

**Nivoplan** should be mixed with clean water and stirred until a smooth, lump-free paste is obtained. It is advisable to use a mechanical stirrer.

One 25-kg bag of **Nivoplan** should be mixed with 5-5.5 litres of water or with 3.5 litres of water and 2 litres of **Planicrete**.

The **Nivoplan** mix remains usable for 2 hours after mixing.

#### Applying the mix

It is invariably advisable to apply a first coat of **Nivoplan** to the substrate so as to ensure perfect coverage and then, without waiting, apply the layer necessary for good levelling, up to a maximum of 3 cm at a time.

**Nivoplan** should be applied with a rendering machine, with a flat trowel or screed (for thick layers) under firm pressure to make the mix adhere well to the substrate.

It is unadvisable to work in temperatures lower than +5°C.

A 1 cm-thick layer of **Nivoplan** is strong enough for laying tiles on substrates with normal absorption after 4-5 hours under normal temperature and humidity conditions.

The surfaces can be painted over after at least 2 weeks.

This time becomes longer in winter and shorter in summer.

When applying on walls directly exposed to the sun or wind, it is advisable to wet the surface of the **Nivoplan** to avoid premature curing.

#### Cleaning

Tools and hands may be cleaned using water before the product sets.

#### **PACKAGING**

**Nivoplan** is supplied in multi-layer-paper bags of 25 kg and should be stored in a

dry place, where it will remain undeteriorated for at least 12 months.

#### **STORAGE**

**Nivoplan**, in its original unopened packaging and in a dry place, can be stored for 12 months.

Manufactured in compliance with the regulations of the 2003/53/EC Directive.

#### **CONSUMPTION**

Consumption depends on the thickness of the layer but is  $1.4 \text{ kg/m}^2$  per millimetre of thickness (1 cm of thickness =  $14 \text{ kg/m}^2$ ).

## SSAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Nivoplan contains cement, that in contact with sweat or other body fluids produces an irritant alkaline reaction and allergic reactions to those predisposed.

Use protective gloves and goggles. For further and complete information about a safety use of our product please refer to our latest version of the Material Safety Data Sheet.

FOR PROFESSIONAL USE.

#### **WARNING**

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our web site www.mapei.com

All relevant references for the product are available upon request and from www.mapei.com



Spray application of Nivoplan



Screeding



Smoothing with a float





